

# 3375RM

## Polypropylene (PP)

### Description:

POLIMAXX® 3375RM is a Random Copolymer Polypropylene resin for extrusion coating with high flow characteristic. It is suitable for extrusion coating for woven bag, BOPP film and paper with good extrude ability, good adhesive, high clarity and high speed. It also meets the F.D.A. requirement in the code of federal regulations in 21 CFR 177.1520 for food contact.

### Typical applications

Extrusion coating: extrusion coating for BOPP film, woven bag and tarpaulins

Physical Properties:	Method	Unit	Value
Melt Flow Index (2.16 kg/230°C)	ASTM D1238	g/10min.	24
Tensile Strength at Yield	ASTM D638	N/mm <sup>2</sup>	24
Elongation at Yield	ASTM D638	%	35.5
Izod Notched Impact Strength (at 23°C)	ASTM D256	J/m	3.5
Flexural Modulus (1% SECANT)	ASTM D790	MPa	750
Rockwell Hardness	ASTM D785	R-Scale	86
Heat Distortion Temperature (Load 0.45 N/mm <sup>2</sup> )	ASTM D 648	°C	76

### Processing Technique

**Processing Temperature : 190 – 240 °C**

\*\* However, the actual processing conditions depend on mold design, power of machine, equipment and other environments. \*\*

**Remark:** The values presented on the above are typical laboratory average, not to be construed as specifications and may vary within moderate ranges. The applicability or the accuracy of this information or the suitability of our products cannot be guaranteed because the conditions of use on the part or our uses are beyond our control.