High Density Polyethylene Aramco HDPE F5101

Product Description

Aramco HDPE F5101 is a high molecular weight high density polyethylene resin and is typically used in for blown film process especially for thin film applications. This resin has broad molecular weight distribution that makes it easier to process. Films made from this resin typically exhibits high stiffness with excellent impact and toughness characteristics.

Typical Applications

Shopping bags, trash bags, industrial liners.

This product is not intended for use in medical and pharmaceutical applications.

Melt Flow Index (190°C/2.16kg) g/10min ASTM D1238 0.05 Melt Flow Index (190°C/21.6kg) g/10min ASTM D1238 9.3 Density g/cm³ ASTM D792 Method A 0.951 Film Properties(2) Tensile Strength at Yield MD MPa ASTM D882 35 Tensile Strength at Break MD MPa ASTM D882 75 Tensile Elongation at Break MD % ASTM D882 520 Tensile Elongation at Break MD MPa ASTM D882 560 1% Secant Modulus MD MPa ASTM D882 1140 Elmendorf Tear Strength MD gf ASTM D1922 78 Dart Drop Impact f ASTM D1709 245 Thermal Properties(2) Vicat Softening Temperature @10N °C ASTM D1525 126	Physical Properties		Unit	Test Method	Value ⁽¹⁾	
Density g/cm³ ASTM D792 Method A 0.951	Melt Flow Index (190°C/2.16kg)		g/10min	ASTM D1238	0.05	
Tensile Strength at Yield	Melt Flow Index (190°C/21.6kg)		g/10min	ASTM D1238	9.3	
Tensile Strength at Yield	Density		g/cm³	ASTM D792 Method A	0.951	
Tensile Strength at Yield TD MPa ASTM D882 30 Tensile Strength at Break MD MPa ASTM D882 75 Tensile Elongation at Break MD % ASTM D882 550 TD MD ASTM D882 560 1% Secant Modulus MD ASTM D882 1140 Elmendorf Tear Strength MD ASTM D1922 78 Dart Drop Impact f ASTM D1709 245 Thermal Properties(2)	Film Properties ⁽²⁾					
Tensile Strength at Break	Tensile Strength at Yield		MPa	ASTM D882		
Tensile Elongation at Break TD % ASTM D882 560 1% Secant Modulus MD 990 TD MPa ASTM D882 1140 Elmendorf Tear Strength MD 11 78 Dart Drop Impact f ASTM D1709 245 Thermal Properties ⁽²⁾	Tensile Strength at Break		MPa	ASTM D882		
1% Secant Modulus TD MPa ASTM D882 1140 Elmendorf Tear Strength MD gf ASTM D1922 78 Dart Drop Impact f ASTM D1709 245 Thermal Properties ⁽²⁾	Tensile Elongation at Break		%	ASTM D882		,
Elmendorf Tear Strength TD gf ASTM D1922 78 Dart Drop Impact f ASTM D1709 245 Thermal Properties ⁽²⁾	1% Secant Modulus		MPa	ASTM D882		
Thermal Properties ⁽²⁾	Elmendorf Tear Strength		gf	ASTM D1922		
	Dart Drop Impact		f	ASTM D1709	245	
Vicat Softening Temperature @10N °C ASTM D1525 126	Thermal Properties ⁽²⁾					
	Vicat Softening Temperature @10N		°C	ASTM D1525	126	

⁽¹⁾ Typical values only, not to be construed as specification limits $% \left(1\right) =\left(1\right) \left(1\right$

Processing conditions: Recommended melt temperature: 180 – 220 °C

Storage and handling: Aramco HDPE F5101 should be stored in a dry cool place with adequate ventilation and protected from UV-light at temperature below 50 °C

Food Contact and other Regulations: Aramco HDPE F5101 resins are suitable for food contact applications. Detailed information is provided in Material Safety Datasheet and for additional specific information, please contact Aramco Trading for certificates.

Disclaimer: © Saudi Aramco Products Trading Company. All information supplied by or on behalf Saudi Aramco Products Trading Company in relation to its products, whether in the nature of data, recommendations or otherwise, is supported by research and believed reliable, but Saudi Aramco Products Trading Company assumes no liability whatsoever in respect of application, processing or use made of the provided information or products, or any consequence thereof. The user is solely responsible and liable with respect to the application, processing or use of the provided information or products. Trading Company for any infringement of the rights owned or controlled by a third party in intellectual, industrial or other property by reason of the application, processing or use of the provided information or products by the user. To the extent the user is entitled to disclose and distribute this document, the user may forward, distribute, and/or photocopy this copyrighted document only if unaltered and complete, including all of its headers, footers, disclaimers and other information.

⁽²⁾ Film fabrication conditions: Extruder 50mmφ, Die 120mmφ, Die Gap 1.35mm, Temp 200°C, Output 50kg/hr., BUR 4.0, Thickness 20μm, Neck Height 840mm