

LL7420A

Linear Low Density Polyethylene Resin

Special Characteristics : InnoPlus LL7420A resin is a linear low density polyethylene with butene comonomers, without slip and antiblock. This grade offers an outstanding excellent draw down in both blown and cast film processing. Films extruded from InnoPlus LL7420A have high tensile, gloss and good toughness properties. It can be used for blending with other polyethylene types, such as HDPE and LDPE.

Typical Applications : InnoPlus LL7420A is recommended for producing the stretch films, liners, industrial bags, refuse sacks and garbage bags.

Typical Properties :

Properties	InnoPlus LL7420A	Unit	Test Method
<i>Physical Properties</i>			
Melt Index (190 °C, 2.16 kg)	2.0	g/10 min	ASTM D1238
Density	0.918	g/cm ³	ASTM D792
Melting Point	121	°C	ASTM D3418
Vicat Softening Point	97	°C	ASTM D1525
<i>Film Properties*</i>			
Tensile Strength at Break (MD/TD)	31 / 23	MPa	ASTM D882
Elongation at Break (MD/TD)	600 / 800	%	ASTM D882
Tensile Modulus, 1% Secant (MD/TD)	195 / 220	MPa	ASTM D882
Dart Impact Strength	85	g	ASTM D1709
Tear Strength (MD/TD)	60 / 135	g	ASTM D1922
Haze	10	%	ASTM D1003
Gloss (45°)	50	-	ASTM D2457
* film properties obtained from 25 microns film which was blown film extruded at blow up ratio 2			

Processing Condition :

The recommended temperature setting is in the range of

- 160 - 180 °C for extruder and 170 - 190 °C for die zone. (blown film)
- 210 - 270 °C for extruder and 260 - 270 °C for die zone. (cast film)

Note : Properties reported here are typical values of the product, not to be considered as specifications.